



PIDILITE INDUSTRIES LIMITED

Marketing Division: P.B. No. 17411, Andheri (East), Mumbai 400 059 (India)

TECHNICAL DATA SHEET

FEVICOL FLOORFIX SUPER TAC

Fevicol Floorfix Super Tac is a solvent free water base acrylic tackifier (Pressure Sensitive Adhesive) for dry- lay floor tiles and carpets. While providing high level anti slip stop, it will also allow removal of the carpet tiles to facilitate access to electrical telephonic lines etc., as well as allowing the replacement of worn, damaged or stained carpet tiles.

TECHNICAL DATA:

- Appearance: Creamish colour viscous liquid
- Base: Acrylic emulsion
- Glue Application: by trowel or sponge roller
- Solids: 54-56
- Viscosity: 250 -400 PS
- Flammability: Non- flammable in wet state
- Coverage: 15-20 sq. meters per kg when applied by roller with 30 % dilution (depending upon substrate)
5-6 Sq. meter per kg when applied by trowel no # A4
- Drying time: 30- 120 minutes depending upon climatic conditions
- Bonding time duration: Indefinite when kept clean
- VOC content: complies with LEED EQ 4.1 requirements of carpet adhesives.

AREA OF USAGE:

- Suitable for bonding of carpets with PVC, foam and bitumen back tiles over existing floors or raised flooring
- Also suitable for under lay

FEATURES:

- Easy replacement of floor covering is possible
- VOC in compliance with LEED EQ 4.1
- Solvent free product

- High degree of tackiness

APPLICATION GUIDE:

Preparing the substrate:

1. Substrates must be dry, absorbent, even, sound, mechanically strong, free of dust, loose particles, cracks, Paint, wax, oil, rust, traces of gypsum or other material that can interfere with bonding.
2. Cement floor pH should not exceed 10 and moisture content should be 2.5-3 %

ADHEISVE APPLICATION:

1. Stir well before use
2. Apply glue by notch trowel (#A 4)
3. Fevicol Floorfix Super Tac can be applied by roller. In this case it is necessary to dilute the adhesive with **20-30 % water**.
4. Wait until glue dries completely. Waiting time can vary from 30 minutes to 2 hours depending on ambient temperature, type of substrate, dilution, and quantity of adhesive spread.
5. The final strength of adhesive depends upon the applied amount, absorbency of substrate and type of tile backing.

CLEAN UP:

- Tool and equipment's can be cleaned with water
- Remove fresh spots of adhesive with a moist cloth
- Fully cured Fevicol Floorfix Super TAc cannot be re-emulsified and must be removed mechanically.

SHELF LIFE:

24 months when stored in original bucket at 30°C

NOTE: A detailed MSDS is available on request.

Note: We recommend that before using our product in full-scale production, the customer should make his own tests to determine the suitability of the product under his operating conditions. As the circumstances under which our products are stored, handled and used are beyond our control, we cannot assume any responsibility for their misuse by the customer.

(Revision No 03, 16/06/2019)